



TECHNICAL DATA SHEET
KOSMIC SHIMMER SILVER BASE MC

KOSMIC SHIMMER SILVER BASE MC

Description

Kosmic Shimmer Silver Base MC is a single component metallic finish for wood. Provide with ease application, fast drying, excellent outdoor weather-ability and excellent orientation. This Base will be used for colour tinting purposes using tinters from ATS machine.

Product

RIFSQ104L01I

Woods for which the product is suitable


- Non resinous softwood
- Light colour hardwood
- MDF

Product Properties

In Can Appearance : Free Flowing Metallic Liquid
 In Can Viscosity : 100 ± 10 secs @30°C Ford cup B4
 Non Volatile Material : 36 ± 2%
 WPL (weight per litre) : 1 ± 0.02 gm./ml
 Shelf Life : 1 Year (from date of mfg.)

**** Note – Product shelf life is determined at minimum temperature 10°C (50° F) maximum temperature 35°C (95°F)**
 -In 800 ml. Shimmer Silver Base MC toner to be added from ATS machine up to 10- 50ml.

Mixing Ratio



4 Parts by Volume – Kosmic Shimmer Silver Base MC
 1 Part by volume – Nax Super hardener
 30 - 35% by Volume- Pu Medium Thinner

Complementary Products

Quantities

Hardener	Super Hardener	In weight w/w %	24.5	
		In volume v/v %	25	
Solid Content %		44± 2		
Paint Mixing Qty(by volume & Weight)	Paint by Volume	Base-500 ml	Hardener-125 ml	Thinner-210 ml
	Paint By Weight	Base-500 gm	Hardener-122.5 gm	Thinner- 212 gm
Thinner	Pu Medium Thinner	In weight w/w %	34	
		In volume v/v %	34	

READY TO USE PRODUCT PROPERTIES

	Solid content 1st +2nd component(%)	37 ± 2
	Pot life @ 30°C	2.5 - 3 hrs
	Viscosity (Ford 4 cup)	18 ± 2
Code/Gloss	CODE	Gloss level EN ISO 2813 (angle measurement 60°)
	WPTCU011L01I	50 - 60 unit

Surface Preparation




- Make Sure Proper Sanding of the Panel is done with #220-320 Mess
- No dust Particle should be present on the surface
- Remove all dust from surface using clean quality rags or wiping towels.
- Apply 2 Coat of Kosmic white filler,
- Sand the panel (#320-400 Mess) Properly, make sure no orange peel is seen on the panel.
- Apply 2 Coats of Kosmic Shimmer Silver Base MC

Spray Gun Set Up



- Gravity Feed (Orifice) – 1.4 – 1.6 mm
- Air Pressure – 35-40 psi (2.4 – 2.75 Bar) at spray gun inlet.

Application



Spray Gun


- 2 Coat Applications
- (65 – 75) μ - spray Gun 1.4mm / (85-100) μ Spray Gun Nozzle – 1.6mm For

- Flash Off in Between Coats – 2 -3 min @30°C, RT – 65%

Products and Additives

Kosmic Shimmer Silver Base MC
 Nax Super Hardener
 Pu Medium Thinner


Product Properties After Application



- Dust Free Time : 15 - 20 min
- Touch Dry : 1 - 1.5 hours
- Handability Dry : 2 - 3 hours @30°C

*Note – All results are considerable at RT – 30°C & RH – 65%.

Coverage



Theoretical Coverage – 50-55 Sq. ft. per litre At 40 -50 Microns DFT at 30C. The practical material usage depends on many factors i.e. shape of the object, roughness of the surface, application techniques, application pressure, application method and application circumstances.

Product Performance Properties

- Gloss - Semi Glossy Matallic finish
- Orange Peel – No orange Peel
- Cross Hatch adhesion – 2 mm (100*100mm)
- PU Thinner Rub test – 20 times -Pass
- Finish-smooth
- Humidity Resistance – 240 C x RH 90% x 500hrs.
- Water resistance - 40°C/500 Hrs
- Alkali TEST (5% Nacl solution)– Pass
- Acid Test (5%H2SO4)- Pass
- PU Thinner Rub test – 20 times-Pass

**Note – Product Shelf Life is determined when product is stored unopened at 30°C(86°F). Avoid Much temperature Fluctuation.